Purell SM170G

聚丙烯无规共聚物

LyondellBasell Industries



ides.com/prospector

Technical Data

产品说明

台休

Purell SM170G is a soft polyolefinic resin combining the typical advantages of polypropylene random and heterophasic copolymers. This resin is used at customers for transparent packaging of pharamceuticals produced in BFS technology or EBM conversion.

Purell SM170G exhibits an excellent balance of toughness and transparency at a very good softness combined with low amount of extractables. It features also good heat distortion resistance.

Purell SM170G is suitable for food contact. Purell SM170G is a soft polyplefinic resin combining the typical advantages of polypropylene random and heterophasic copolymers. This resin is used at customers for transparent packaging of pharamceuticals produced in BFS technology or EBM conversion.

Purell SM170G exhibits an excellent balance of toughness and transparency at a very good softness combined with low amount of extractables. It features also good heat distortion resistance.

Purell SM170G is suitable for food contact.

Without exception, all potential activities for applications in the pharmaceutical, medical device, laboratory and diagnostics area have to be discussed with the relevant LyondellBasell Technical and Business contacts first.

| 忠体 | | | |
|---------------------|---|---|---|
| 材料状态 | • 已商用:当前有效 | | |
| 资料1 | Technical Datasheet (English) Processing - Mold Shrink (English) Processing - Extrusion (English) Processing - Injection Molding (English) | | |
| 搜索 UL 黄卡 | LyondellBasell Industrie | es | |
| 供货地区 | 北美洲非洲和中东 | 拉丁美洲欧洲 | • 亚太地区 |
| 性能特点 | 低萃取物良好的柔韧性耐高压加热性 | 耐热性,中等清晰度,高韧性良好 | • 柔软 • 食品接触的合规性 • 无规共聚物 |
| 用途 | 包装薄膜 | 瓶子小瓶 | 药品包装医疗/护理领域的应用 |
| 加工方法 | • 挤出吹塑成型 | | |
| | | 额定值 单位制 | 测试方法 |
| 密度 | | 0.900 g/cm ³ | ISO 1183 |
| 熔流率 (230°C/2.16 kg) | | 1.5 g/10 min | ISO 1133 |
| 机械性能 | | 额定值 单位制 | 测试方法 |
| 拉伸模量 | | 650 MPa | ISO 527-2 |
| 拉伸应力 (屈服) | | 21.0 MPa | ISO 527-2 |
| 拉伸应变 | | | ISO 527-2 |
| 屈服, 23°C | | 15 % | |
| 断裂, 23°C | | > 400 % | |
| 中击性能 | | 额定值 单位制 | 测试方法 |
| 悬壁梁缺口冲击强度 | | | ISO 180 |
| -20°C | | 4.0 kJ/m² | |
| 0°C | | 11 kJ/m² | |
| 23°C | | 51 kJ/m² | |
| 热性能 | | 额定值 单位制 | 测试方法 |
| 热变形温度 | | | |
| 0.45 MPa, 未退火 | | 63.0 °C | ISO 75-2/B |
| 1.8 MPa, 未退火 | | 40.0 °C | ISO 75-2/A |
| 维卡软化温度 | | 125 °C | ISO 306/A50 |
| | | | |

UL and the UL logo are trademarks of UL LLC © 2013. All Rights Reserved. UL IDES | 800-788-4668 or 307-742-9227 | www.ides.com.

文件号: TDS-150708-zh 文件建立日期: 2013年5月26日 添加到 Prospector: 2011年6月 上次更新: 2011/6/2

Purell SM170G

聚丙烯无规共聚物

LyondellBasell Industries



ides.com/prospector

1通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料;不过您可以从供应商处了解最新资料。

2 一般属性:这些不能被视为规格。

UL and the UL logo are trademarks of UL LLC © 2013. All Rights Reserved. UL IDES | 800-788-4668 or 307-742-9227 | www.ides.com.

文件号: TDS-150708-zh 文件建立日期: 2013年5月26日 添加到 Prospector: 2011年6月 上次更新: 2011/6/2

Purell SM170G

聚丙烯无规共聚物

LyondellBasell Industries



ides.com/prospector

购买地点

供应商

LyondellBasell Industries

Wilmington, DE USA 电话: 713-309-7200

Web: http://polymers.lyondellbasell.com/portal/site/basell/

分销商

ALBIS Plastic

ALBIS PLASTIC is a pan-European distribution and compounding company. Contact ALBIS PLASTIC for availability of individual products per country.

电话: +49-40-78105-0 Web: http://www.albis.com/ 可用性: Europe

Nexeo Solutions

电话: 800-531-7106

Web: http://www.nexeosolutions.com/

可用性: North America

Ultrapolymers

Ultrapolymers is a Pan European distribution company. Contact Ultrapolymers for availability of individual products by country.

电话: +32-11-57-95-57

Web: http://www.ultrapolymers.com/

可用性: Belarus, Belgium, Bosnia and Herzegovina, Bulgaria, Croatia, Denmark, Estonia, Finland, France, Germany, Hungary, Ireland, Italy, Latvia, Lithuania, Macedonia, Netherlands, Norway, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Turkey, United Kingdom

文件号: TDS-150708-zh

文件建立日期: 2013年5月26日 添加到 Prospector: 2011年6月 上次更新: 2011/6/2



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



Prospector Plastics Database - www.ides.com/prospector

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.



"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"

- Birgit Elvardt Bader, Production Manager, Micotron

Power Searches

Property Search – select plastics by 500 key properties and design parameters.

Alternative Resins Search - find replacement plastics within minutes.

Automotive Plastics Search – easily locate automotive approved plastics.

Curve Data – view, overlay and export curve data.



Material Data Management - www.ides.com/datasheets

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."

- Kevin Chase, Owner & President, Chase Plastics



Advertising - www.ides.com/advertise

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.

For more information, call: 800.788.4668 or 307.742.9227 ext. 220